

## TIANYA- CMC Mining Flotation Grade Specification

### CMC Mining Flotation Grade Specification

Types	Specification						
	Viscosity, 2% solution	Degree of Substitute	Purity, %	pH	Moisture Content, %	NaCl, %	Sodium chloroacetate, %
M-1	100-500	≥0.7	≥90	6.5-8.0	≤10	≤10	≤0.7
M-2	100-500	≥0.7	≥80	6.5-8.0	≤10	≤8.0	≤4.0
M-3	100-500	≥0.7	≥70	6.5-8.0	≤10	≤15	≤7.0
M-4	≥500	≥0.7	≥90	6.5-8.0	≤10	≤1.4	≤0.7
M-5	150-400	≥0.7	≥98	6.5-8.0	≤10	≤1.4	≤0.7